

A2 DECORATIVE PANEL

International code: Heraklith A2-M

A2 Decorative panel is a completely finished, square and smooth wood wool panel with an A2 fire rating. This panel has been specially developed for the acoustic and decorative finish of walls and ceilings. Moreover, concrete floors clad with A2 Decorative panels or when installed in a Richter grid ceiling system achieve a fire-resistance of 60 minutes*.



STANDARD VERSION


The A2 Decorative panel is produced with PEFC certified wood and a fibre width of 2 mm as standard. The panels are factory finished with a nature tone colour spray and beveled all round.

* Provided they are processed against solid concrete according to report 16210B or 16211B in accordance with European norm EN 1365-2 / EN 13501-2

PERFORMANCE

 **Fire classification**
A2-s1, d0
★★★★★

 **Sound absorption**
 α_w max. 0.90
★★★★☆

 **Thermal resistance**
 R_D max. 0.55 (50 mm)
★★★★☆

ADVANTAGES

- ✓ Up to 60 minutes fire resistance can be achieved*
- ✓ A2 fire rating, no drop formation and low smoke emissions when burning
- ✓ Good acoustic properties
- ✓ Moisture and mould resistant
- ✓ Aesthetic finish

SPECIFICATIONS

Thickness (mm)	R_D (m ² .K/W)	Weight (kg/m ²)	Length (mm)	Width (mm)	Panels/pallet	Pallet (m ²)
15	0.15	9.0	1200/2000	600	70	50.40 / 82.00
25	0.25	17.5	1200/2000	600	40	28.80 / 48.00
35	0.40	22.0	1000	600	30	18.00
50	0.55	29.0	1000	600	20	12.00

Options

Fibre width	10 mm
Colour	White (RAL 9003) or RAL
Panel variant	Inlay (T 25 mm, W 595 mm, L 1195 mm)

CERTIFICATIONS



Always process our Heraklith wood wool panels according to our processing instructions. These can be found on heraklith.co.uk/downloads



www.heraklith.co.uk

Wood Wool Panel in accordance with EN 13168:2012+A1
WW-EN 13168-L2-W1-T1-S2-P2-CS(10/Y)200-CI3

TECHNICAL INFORMATION

Properties	Symbol	Description	Unit	Norm
Fire class	-	A2-s1, d0	-	EN 13501-1
Fire resistance	-	REI 60 (Provided they are processed against solid concrete according to report 16210B or 16211B)	-	EN 13501-2
Heat conductivity coefficient	λ	Wood wool: 0.085	[W/mK]	EN 12667
Compressive strength	CS	(D \leq 25mm) \geq 200, (D > 25mm) \geq 150	[kPa]	EN 826
Chloride levels	Cl	CI3	-	EN 13168
Tolerances	-	Thickness (T1) Length (L2) Width (W1) Squareness (S2) Flatness (P1)	[mm]	EN 13168
		+3/-2 +3/-5 \pm 3 \leq 2 \leq 6		
Edge finishing	Bevelled on all sides			
DoP-code	W4302APCPR (www.dopki.com)			

SOUND ABSORPTION COEFFICIENT

Panel type	F(Hz)	125	250	500	1000	2000	4000	α_w	NRC	SAA	Report number
1. Concrete 2. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.06	0.13	0.27	0.63	0.91	0.66	0.35	0.50	-	A 2518-3-RA-001
1. Concrete 2. Heraklith® [1mm], 25mm	α_s (1/1 octave)	0.08	0.16	0.31	0.60	0.94	0.72	0.35	0.50	-	A 2828-2E-RA-001
1. Concrete 2. Cavity, 175mm 3. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.21	0.56	0.65	0.52	0.65	0.82	0.60	0.60	-	A 2828-2E-RA001
1. Concrete 2. Cavity, 135mm 3. Mineral wool, 40mm 4. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.44	0.87	0.27	0.90	0.84	0.95	0.90	0.85	-	A 2828-2E-RA001
1. Concrete 2. Heraklith® [2mm], 35mm	α_s (1/1 octave)	0.09	0.16	0.35	0.81	0.77	0.76	0.40	0.50	-	A 2518-3-RA-001
1. Concrete 2. Heraklith® [2mm], 50mm	α_s (1/1 octave)	0.15	0.33	0.62	0.87	0.75	0.85	0.60	0.65	-	A 2518-3-RA-001

Sound absorption tests have been executed in accordance with the norm ISO 11654/ ASTM-C423

Do you want more information? Please contact us

Knauf Insulation B.V.

Dakota 7
5126 RL Gilze

Tel: + 31 (0)162 - 42 12 45
e-mail: info.nl@knaufinsulation.com

www.heraklith.co.uk

Our general sales and delivery conditions apply to all our offers, communications and agreements, notwithstanding any provision to the contrary that can be found on our order forms or elsewhere. An overview of our general terms and conditions can be found on: heraklith.co.uk/downloads. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V1-EN 08/2021

Heraklith® is a registered trademark of

