

A2 DECORATIVE PANEL

International code: Heraklith A2-M

DESCRIPTION




Heraklith® | A2 Decorative panel is a completely finished, square and smooth wood wool panel with an A2 fire rating. This panel has been specially developed for the acoustic and decorative finish of walls and ceilings. Moreover, concrete floors clad with A2 Decorative panels or when installed in a Richter grid ceiling system achieve a fire-resistance of 60 minutes*.



STANDARD VERSION

The Heraklith® A2 Decorative panel is produced with 100% FSC certified wood and a fibre width of 2 mm as standard. The panels are factory finished with a nature tone colour spray and beveled all round.

PERFORMANCE

 Fire classification A2-s1, d0 ★★★★★	 Sound absorption $\alpha_w \geq 0.35$ (25 mm) ★★★★★☆	 Thermal resistance $R_b = 0.55$ (50 mm) ★★★★★☆
--	---	---

* Provided they are treated in accordance with Classification Report no. 16211B in accordance with European norm EN 1365-2

ADVANTAGES

- ✓ Excellent fire-resistant properties (60 minutes)
- ✓ Good acoustic properties
- ✓ A2 fire rating, no drop formation and low smoke emissions when burning
- ✓ Moisture and mould resistant
- ✓ Aesthetic finish

SPECIFICATIONS

Panel thickness (T) (mm)	R _D (m ² .K/W)	Weight (kg/m ²)	Length (L) (mm)	Width (W) (mm)	Panels/pallet	Pallet (m ²)
15	0.15	8.5	1200/2000	600	70	50.40 / 84.00
25	0.25	11.5	1200/2000	600	40	28.80 / 48.00
35	0.40	14.5	1000	600	30	18.00
50	0.55	19.5	1000	600	20	12.00

Options

Finishing	10 mm
Colour	White (RAL 9003) or RAL
Panel variant	Inlay (T 25 mm, W 595 mm, L 1195 mm)

CERTIFICATIONS



Always process our Heraklith wood wool panels according to our processing instructions. These can be found on www.heraklith.co.uk/processinginstructions



www.heraklith.co.uk

Wood Wool Panel in accordance with EN 13168:2012+A1
WW-EN 13168-L2-W1-T1-S2-P2-CS(10/Y)200-CI3

TECHNICAL INFORMATION

Properties	Symbol	Description					Unit	Norm
Fire classification	-	A2-s1, d0					-	EN 13501-1
Fire-resistance	-	REI 60 (when mounted according to classification report no.: 16210B or 16211B)					-	EN 13501-2
Heat conductivity coefficient	λ	Wood wool: 0.090					[W/mK]	EN 12667
Compressive strength	σ_m	≥ 200					[kPa]	EN 826
Chloride levels	C	CI3					-	EN 13168
Tolerances	-	Thickness (T1)	Length (L2)	Width (W1)	Squareness (S2)	Flatness (P1)	[mm]	EN 13168
		[D \leq 100] +3/-2	+3/-5	± 3	≤ 2	≤ 6		
DoP-code	W4302APCPR (www.dopki.com)							

SOUND ABSORPTION COEFFICIENT

Panel type	F(Hz)	125	250	500	1000	2000	4000	α_w	NRC	SAA	Report number
1. Concrete 2. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.06	0.13	0.27	0.63	0.91	0.66	0.35	0.50	-	A 2518-3-RA-001
1. Concrete 2. Heraklith® [1mm], 25mm	α_s (1/1 octave)	0.08	0.16	0.31	0.60	0.94	0.72	0.35	0.50	-	A 2828-2E-RA-001
1. Concrete 2. Cavity, 175mm 3. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.21	0.56	0.65	0.52	0.65	0.82	0.60	0.60	-	A 2828-2E-RA001
1. Concrete 2. Cavity, 135mm 3. Mineral wool, 40mm 4. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.44	0.87	0.27	0.90	0.84	0.95	0.90	0.85	-	A 2828-2E-RA001
1. Concrete 2. Heraklith® [2mm], 35mm	α_s (1/1 octave)	0.09	0.16	0.35	0.81	0.77	0.76	0.40	0.50	-	A 2518-3-RA-001
1. Concrete 2. Heraklith® [2mm], 50mm	α_s (1/1 octave)	0.15	0.33	0.62	0.87	0.75	0.85	0.60	0.65	-	A 2518-3-RA-001

Sound absorption tests have been executed in accordance with the norm ISO 11654/ ASTM-C423

Do you want more information? Please contact us

Knauf Insulation B.V.

PO Box 375
4900 AJ Oosterhout
The Netherlands

Tel: + 31 (0)162 - 42 12 45
e-mail: info.nl@knaufinsulation.com

www.heraklith.nl

Our general sales and delivery conditions apply to all our offers, communications and agreements, notwithstanding any provision to the contrary that can be found on our order forms or elsewhere. An overview of our general terms and conditions can be found on: www.heraklith.co.uk/content/downloads-documents. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V1-EN 06/2018

Heraklith® is a registered trademark of

KNAUF INSULATION