

BASIC


 International code: Heraklith C

DESCRIPTION

Our Heraklith® | Basic panel is a wood wool panel with a particularly robust industrial look.

STANDARD VERSION


The Heraklith® | Basic panel is produced with 100% FSC certified wood and a fibre width of 2 mm as standard. The panels will be delivered with straight edges and without any factory finishing.



PERFORMANCE

 **Fire classification**
B-s1, d0
★★★★☆

 **Sound absorption**
 α_w max. 0,90
★★★★☆

 **Thermal resistance**
 R_D max. 0.60 (50 mm)
★★★★☆

ADVANTAGES

- ✓ Good sound absorption properties
- ✓ Natural, robust look
- ✓ Moisture and mould resistant

SPECIFICATIONS

Panel thickness (T) (mm)	R_D (m ² .K/W)	Weight (kg/m ²)	Length (L) (mm)	Width (W) (mm)	Panels/pallet	Pallet (m ²)
15	0.15	8.5	2000	600	70	84.00
25	0.30	11.5	2000	600	40	48.00
35	0.40	14.5	2000	600	29	34.80
50	0.60	19.5	2000	600	20	24.00

CERTIFICATIONS



Always process our Heraklith wood wool panels according to our processing instructions. These can be found on heraklith.co.uk/downloads



www.heraklith.co.uk

Wood Wool Panel in accordance with EN 13168:2012+A1
WW-EN 13168-L1-W1-T1-S1-P1-CS(10/Y)150/200-CI1

TECHNICAL INFORMATION

Properties	Symbol	Description					Unit	Norm
Fire class	-	B-s1,d0					-	EN 13501-1
Heat conductivity coefficient	λ	Wood wool: 0.080					[W/mK]	EN 12667
Compressive strength	$\bar{\sigma}_m$	(D ≤ 25mm) ≥ 200, (D > 25mm) ≥ 150					[kPa]	EN 826
Chloride levels	C	CI1					-	EN 13168
Tolerances	-	Thickness (T1)	Length (L1)	Width (W1)	Squareness (S1)	Flatness (P1)	[mm]	EN 13168
		+3/-2	+5/-10	± 3	≤ 4	≤ 6		
Edge finishing wood wool	Straight edges							
DoP-code	W4302APCPR (www.dopki.com)							

SOUND ABSORPTION COEFFICIENT

Panel type	F(Hz)	125	250	500	1000	2000	4000	α_w	NRC	SAA	Report number
1. Concrete 2. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.06	0.13	0.27	0.63	0.91	0.66	0.35	0.50	-	A2518-3-RA-001
1. Concrete 2. Heraklith® [1mm], 25mm	α_s (1/1 octave)	0.08	0.16	0.31	0.60	0.94	0.72	0.35	0.50	-	A2828-2E-RA-001
1. Concrete 2. Cavity, 175mm 3. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.21	0.56	0.65	0.52	0.65	0.82	0.60	0.60	-	A 2828-2E-RA001
1. Concrete 2. Cavity, 135mm 3. Minerale wol, 40mm 4. Heraklith® [2mm], 25mm	α_s (1/1 octave)	0.44	0.87	0.87	0.90	0.84	0.95	0.90	0.85	-	A 2828-2E-RA001
1. Concrete 2. Heraklith® [2mm], 35mm	α_s (1/1 octave)	0.09	0.16	0.35	0.81	0.77	0.76	0.40	0.50	-	A2518-3-RA-001
1. Concrete 2. Heraklith® [2mm], 50mm	α_s (1/1 octave)	0.15	0.33	0.62	0.87	0.75	0.85	0.60	0.65	-	A2518-3-RA-001

Sound absorption tests have been executed in accordance with the norm ISO 11654/ ASTM-C423

Do you want more information? Please contact us

Knauf Insulation B.V.

PO Box 375
4900 AJ Oosterhout
The Netherlands

Tel: + 31 (0)162 - 42 12 45
e-mail: info.nl@knaufinsulation.com

www.heraklith.nl

Our general sales and delivery conditions apply to all our offers, communications and agreements, notwithstanding any provision to the contrary that can be found on our order forms or elsewhere. An overview of our general terms and conditions can be found on: heraklith.co.uk/downloads. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V2-EN 11/2018

Heraklith® is a registered trademark of

KNAUFINSULATION