

# HERAFOAM

Herafoam is a wood wool panel combined with a rigid foam insulation board that has a tongue and groove connection that supports very easy installation. This panel is very well suited for concrete ceilings and walls in renovation and new development projects that require high thermal performance and limited thickness.

## STANDARD VERSION

Herafoam is produced with PEFC certified wood and a fibre width of 2 mm as standard. The panels are delivered unpainted as a standard in the natural, warm tones of wood. Our panels are factory finished with lapjoints and beveled all round. The insulation has a tongue and groove connection.



## PERFORMANCE



**Fire classification**

B-s1, d0



**Sound absorption**

$\alpha_w = 0.30$



**Thermal resistance**

$R_D$  max. 7.10 (170 mm)



## ADVANTAGES

- ✓ Lightweight wood wool panel
- ✓ Very high thermal insulation values with low panel thickness
- ✓ 2 point mounting in combination with tongue and groove ensures an easy and flat mounting process
- ✓ Moisture and mould resistant
- ✓ Aesthetic finish and insulation with one panel

## SPECIFICATIES

Thickness (mm)	Composition mm [HW/PIR]	$R_D$ ( $m^2 \cdot K/W$ )	Weight ( $kg/m^2$ )	Length (mm)	Width (mm)	Panels/pallet	Pallet ( $m^2$ )
50	10/40	1.55	7.3	985	590	44	25.57
80	10/70	2.90	8.6	985	590	26	15.11
105	10/95	4.10	9.4	985	590	22	12.79
130	10/120	5.25	10.1	985	590	16	9.30
150	10/140	6.20	10.7	985	590	14	8.14
170	10/160	7.10	11.3	985	590	12	6.97

### Options

Fibre width	1,0 mm
Colour	Wit (RAL9003), RAL

## CERTIFICATIONS



Always process our Heraklith wood wool panels according to our processing instructions. These can be found on [heraklith.co.uk/downloads](http://heraklith.co.uk/downloads)



[www.heraklith.co.uk](http://www.heraklith.co.uk)

Wood Wool Combi Panel in accordance with EN 13168:2012+A1  
WW-C/2 PU-EN13168-L2-W1-S1-T1-P1-CS(10/Y)150-C11

## TECHNISCHE INFORMATIE

Properties	Symbol	Description					Unit	Norm
Fire classification	-	B-s1,d0 *					-	EN 13501-1
Heat conductivity coefficient	$\lambda$	Wood wool: 0,090 / PIR: 0,0275 - 0,0215					[W/mK]	EN 12667
Compressive strength	CS	$\geq 150$					[kPa]	EN 826
Chloride levels	Cl	Cl1					-	EN 13168
Tolerances	-	Thickness	Length (L2)	Width (W1)	Squareness (S1)	Flatness (P1)	[mm]	EN 13168
		[D $\leq$ 100 ] +3/-2	+3/-5	$\pm 3$	$\leq 4$	$\leq 6$		
Finishing insulation		Tongue and groove						
Finishing wood wool		Bevelled all round						
DoP-code		4010_HERAFOAM ( <a href="http://www.heraklith.co.uk">www.heraklith.co.uk</a> )						

\* Mounted directly to concrete

## SOUND ABSORPTION COEFFICIENT\*

Panel type	F(Hz)	125	250	500	1000	2000	4000	$\alpha_w$	NRC	SAA	Report number
Herafoam (2mm), 50mm	$\alpha_s$ (1/1 octave)	0.03	0.08	0.22	0.29	0.39	0.75	<b>0.30</b>	0.20	0.24	A 3598-3E-RA001
Herafoam (2mm), 100mm	$\alpha_s$ (1/1 octave)	0.04	0.11	0.28	0.20	0.40	0.77	<b>0.30</b>	0.25	0.25	A 3598-3E-RA001
Herafoam (2mm), 150mm	$\alpha_s$ (1/1 octave)	0.07	0.19	0.28	0.23	0.43	0.80	<b>0.30</b>	0.25	0.28	A 3598-3E-RA001

Sound absorption tests have been executed in accordance with the norm ISO 11654/ ASTM-C423

\* Mounted directly to concrete

## Do you want more information? Please contact us

### Knauf Insulation B.V.

PO Box 375  
4900 AJ Oosterhout  
The Netherlands

Tel: + 31 (0)162 - 42 12 45  
e-mail: [customerservice.nl@knaufinsulation.com](mailto:customerservice.nl@knaufinsulation.com)

[www.heraklith.co.uk](http://www.heraklith.co.uk)

Our general sales and delivery conditions apply to all our offers, communications and agreements, notwithstanding any provision to the contrary that can be found on our order forms or elsewhere. An overview of our general terms and conditions can be found on: [heraklith.co.uk/downloads](http://heraklith.co.uk/downloads). Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V5-EN 04/2020

Heraklith® is a registered trademark of

**KNAUF INSULATION**