

TEKTALAN A2

International code: Tektalan A2-E-31-035/2 - Tektalan A2-035/2

DESCRIPTION

Heraklith® | Tektalan A2 combines wood wool with a rock mineral wool insulation. This panel combines excellent fire-resistant properties with outstanding thermal and acoustic performance. Extensive international fire tests have shown that solid concrete floors covered with Tektalan A2 panels, can provide 180 minutes of fire resistance¹. Tektalan A2 works as a heat shield, ensuring the integrity of the structure for a longer period in the event of a fire.



STANDARD VERSION

The Heraklith® Tektalan A2 is produced with 100% FSC certified wood and a fibre width of 2 mm as standard. The panels are factory finished with a nature tone colour spray and beveled all round.

PERFORMANCE

Fire classification
A2-s1, d0
★★★★★

Sound absorption
 α_w max. 1,00
★★★★★

Thermal resistance
 R_D max. 6.40 (225 mm)
★★★★☆

¹ Provided they are processed against solid concrete according to report 18203 / 18204 in accordance with European norm EN 1365-2 / EN 13501-2

ADVANTAGES

- ✓ Rock mineral wool at the back provided with glass veil: easy to process and less risk of damage
- ✓ Up to 180 minutes fire resistance can be achieved¹
- ✓ A2 fire rating, no drop formation and low smoke emissions when burning
- ✓ Outstanding sound absorption properties
- ✓ Moisture resistant and mould repellent
- ✓ Aesthetic finishing and insulation in one panel

SPECIFICATIONS

Panel thickness (T) (mm)	Composition mm [HW/SW]	R_D (m ² .K/W)	Weight (kg/m ²)	Length (L) (mm)	Width (W) (mm)	Panels/pallet	Pallet (m ²)
50	10/40	1.25	11.0	1000	600	22	13.20
75	10/65	2.00	14.0	1000	600	14	8.40
100	10/90	2.75	17.0	1000	600	11	6.60
125	10/115	3.50	19.5	1000	600	8	4.80
150	10/140	4.20	22.5	1000	600	7	4.20
175	10/165	4.95	25.0	1000	600	6	3.60
200	10/190	5.70	28.5	1000	600	5	3.00
225	10/215	6.40	31.0	1000	600	5	3.00

Options

Finishing	10 mm
Colour	White (RAL 9003) or RAL

CERTIFICATIONS



Always process our Heraklith wood wool panels according to our processing instructions. These can be found on heraklith.co.uk/downloads



www.heraklith.co.uk

Wood Wool Panel in accordance with EN 13168:2012+A1
WW-C2-EN 13168-L2-W1-T1-S2-P1-CS(10/Y)30-TR7,5-C11

TECHNICAL INFORMATION

Properties	Symbol	Description					Unit	Norm
Fire class	-	A2-s1,d0*					-	EN 13501-1
Fire resistance	-	REI 180 (If treated in accordance with Classification Report no. 18203/18204)					-	EN 13501-2
Thermal conductivity coefficient	λ	Wood wool: 0.085 / RMW : 0.034					[W/mK]	EN 12667
Compressive strength	σ_m	≥ 30					[kPa]	EN 826
Tensile strength perpendicular to surface	σ_m	≥ 7.5					[kPa]	EN 1607
Chloride concentration	C	Cl3					-	EN 13168
Tolerances	-	Thickness (T1)	Length (L2)	Width (W1)	Squareness (S2)	Flatness (P1)	[mm]	EN 13168
		[D \leq 100] +3/-2	+3/-5	± 3	≤ 2	≤ 6		
Edge finishing insulation	Straight edges							
Edge finishing wood wool	Bevelled							
DoP-code	W4302CPCPR (www.dopki.com)							

* Mounted directly to concrete

SOUND ABSORPTION COEFFICIENT*

Panel type	F(Hz)	125	250	500	1000	2000	4000	α_w	NRC	SAA	Report number
Tektalan A2 [2mm], 50mm	α_s (1/1 octave)	0.25	0.80	1.00	1.00	0.95	0.80	0.95	0.95	0.95	M104343/02
Tektalan A2 [2mm], 75mm	α_s (1/1 octave)	0.55	0.90	1.00	1.00	0.95	0.80	0.95	0.95	0.96	M104343/02
Tektalan A2 [2mm], 100mm	α_s (1/1 octave)	0.70	0.80	0.95	1.00	1.00	0.85	1.00	0.90	0.93	M104343/02
Tektalan A2 [2mm], 125mm	α_s (1/1 octave)	0.70	0.80	0.95	1.00	1.00	0.90	1.00	0.90	0.93	M104343/02
Tektalan A2 [1mm], 50mm	α_s (1/1 octave)	0.40	0.65	0.75	0.75	0.75	0.85	0.75	0.70	0.73	M104343/03
Tektalan A2 [1mm], 75mm	α_s (1/1 octave)	0.55	0.85	0.95	1.00	1.00	0.95	1.00	0.95	0.97	M104343/03
Tektalan A2 [1mm], 100mm	α_s (1/1 octave)	0.70	0.80	0.95	1.00	1.00	0.95	1.00	0.95	0.96	M104343/03
Tektalan A2 [1mm], 125mm	α_s (1/1 octave)	0.65	0.75	0.95	1.00	1.00	0.95	1.00	0.90	0.93	M104343/03

Sound absorption tests have been executed in accordance with the norm ISO 11654/ ASTM-C423

* Mounted directly to concrete

Do you want more information? Please contact us

Knauf Insulation B.V.

PO Box 375
4900 AJ Oosterhout
The Netherlands

Tel: + 31 (0)162 - 42 12 45
e-mail: info.nl@knaufinsulation.com

www.heraklith.nl

Our general sales and delivery conditions apply to all our offers, communications and agreements, notwithstanding any provision to the contrary that can be found on our order forms or elsewhere. An overview of our general terms and conditions can be found on: heraklith.co.uk/downloads. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V2-EN 11/2018

Heraklith® is a registered trademark of

